

International Designations and Chemical Composition Limits for Aluminum Hardeners

(North American and International Registration Record)



1400 Crystal Drive, Suite 430
Arlington, VA 22202
www.aluminum.org

Issued: December 2018

Supersedes: August 2014

© Copyright 2018, The Aluminum Association, Inc.
Unauthorized reproduction and sale by photocopy or any other method is illegal.

ISSN 2377-6684

Use of the Information

The Aluminum Association has used its best efforts in compiling the information contained in this publication. Although the Association believes that its compilation procedures are reliable, it does not warrant, either expressly or impliedly, the accuracy or completeness of this information. The Aluminum Association assumes no responsibility or liability for the use of the information herein.

All Aluminum Association published standards, data, specifications and other material are reviewed at least every five years and revised, reaffirmed or withdrawn. Users are advised to contact The Aluminum Association to ascertain whether the information in this publication has been superseded in the interim between publication and proposed use.

Contents

	Page
FOREWORD.....	i
SIGNATORIES TO THE DECLARATION OF ACCORD	i
REGISTERED DESIGNATIONS AND CHEMICAL COMPOSITION.....	1-4
Footnotes	5
TABLE OF COLOR CODES FOR ALUMINUM HARDENERS.....	6
Color Codes by Designation.....	7
Color Codes by Alternate Designation	8-9
TABLE OF INACTIVE ALUMINUM HARDENER DESIGNATIONS.....	10
RECOMMENDATION TO THE DECLARATION OF ACCORD.....	11
Appendix A-Terms and Definitions	12
Appendix B-Use of Designations	12
Appendix C-General Guidelines for Determining Compliance with “Sale of Aluminum Hardener” and “Commercial Quantity” for purposes Of Registering Aluminum Hardeners	13
Appendix D-Aluminum Hardener Color Code Scheme	13-14
DECLARATION OF ACCORD	15

FOREWORD

Listed herein are designations and chemical composition limits for aluminum hardeners registered in accordance with the *Recommendation – International Designation System for Aluminum Hardeners*, which is printed on page 11. Additions may be made as required according to the rules outlined in the Declaration of Accord, printed on page 15, and aluminum hardeners will be deleted when no longer in commercial use (See table of Inactive Aluminum Hardeners).

Some of the registered aluminum hardeners may be the subject of a patent or patent application and their listing herein is not to be construed in any way as the granting of a license under such patent rights.

The following organizations are signatories to the Declaration of Accord on the Recommendation:

The Aluminum Association, Inc.
1400 Crystal Drive
Suite 430
Arlington, VA 22202
UNITED STATES OF AMERICA
www.aluminum.org

USA

Aluminium Association of Canada
1010 Sherbrooke Street West, Suite 1600
Montreal, Quebec H3A 2R7
CANADA
www.aac.aluminium.qc.ca

CANADA

Australian Aluminium Council Limited
Level 1, Dickson Square
P.O. Box 63
Dickson, Canberra ACT 2602
AUSTRALIA
www.aluminium.org.au

AUSTRALIA

China Nonferrous Metals Techno-Economic Research Institute
No. 31 Suzhou Street, Haidian District
Beijing, 100080
PEOPLES REPUBLIC OF CHINA
www.cnsmq.com

CHINA

European Aluminium Association
Avenue de Broqueville, 12
B-1150 Brussels
BELGIUM
www.aluminium.org

EAA

Gesamtverband Der Aluminiumindustrie e.V. (GDA)
Am Bonneshof 5
D-40474 Dusseldorf
GERMANY
www.aluinfo.de

GERMANY

Japan Aluminium Association (JAA)
Tsukamoto-Sozan Building
2-15, Ginza 4-Chome
Chuo-Ku, Tokyo 104-0061
JAPAN
www.aluminum.or.jp

JAPAN

ALRO S.A.
116 Pitesti Street
Slatina, Olt County,
230048
ROMANIA
www.alro.ro

ROMANIA