



JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS L 0846 : 2004
(SWTF/JSA)

**Test method for colour fastness
to water**

ICS 59.080.01

Reference number : JIS L 0846 : 2004 (E)

PROTECTED BY COPYRIGHT

This is a preview. [Click here to purchase the full publication.](#)

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee, as the result of proposal for revision of Japanese Industrial Standard submitted by Suga Weathering Technology Foundation (SWTF)/Japanese Standards Association (JSA) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law applicable to the case of revision by the provision of Article 14. Consequently **JIS L 0846 : 1996** is replaced with this Standard.

This revision has been made based on **ISO 105-E01 : 1994 *Textiles—Tests for colour fastness—Part E01 : Colour fastness to water*** for the purposes of making it easier to compare this Standard with International Standard; to prepare Japanese Industrial Standard conforming with International Standard; and to propose a draft of an International Standard which is based on Japanese Industrial Standard.

Attention is drawn to the possibility that some parts of this Standard may conflict with a patent right, application for a patent after opening to the public, utility model right or application for registration of utility model after opening to the public which have technical properties. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying the patent right, application for a patent after opening to the public, utility model right or application for registration of utility model after opening to the public which have the said technical properties.

Date of Establishment: 1967-03-01

Date of Revision: 2004-04-20

Date of Public Notice in Official Gazette: 2004-04-20

Investigated by: Japanese Industrial Standards Committee
Standards Board
Technical Committee on Consumer Life
Products

JIS L 0846 : 2004, First English edition published in 2004-10

Translated and published by: Japanese Standards Association
4-1-24, Akasaka, Minato-ku, Tokyo, 107-8440 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2004

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

Contents

	Page
Introduction	1
1 Scope	1
2 Normative references	1
3 Summary	1
4 Apparatus and materials	1
5 Preparation of composite specimen	3
6 Operation	3
7 Assessment	4
8 Record	4
Annex (informative) Comparison table between JIS and corresponding International Standard	5

Test method for colour fastness to water

Introduction This Japanese Industrial Standard has been prepared based on the fourth edition of **ISO 105-E01 Textiles—Tests for colour fastness—Part E01 : Colour fastness to water** published in 1994, without any modification in technical contents, except additionally including the items (assessment by instrumental method) not stated in the corresponding International Standard.

The portions in this Standard given dotted underlines are the matters in which the contents of the original International Standard have been modified. A list of modifications with the explanations is given in annex (informative).

1 Scope This Standard specifies a method for determining the resistance of the colour of dyed textiles to immersion in water.

Remarks : The International Standard corresponding to this Standard is as follows.

In addition, symbols which denote the degree of correspondence in the contents between the relevant International Standard and **JIS** are IDT (identical), MOD (modified), and NEQ (not equivalent) according to **ISO/IEC Guide 21**.

ISO 105-E01 : 1994 *Textiles—Tests for colour fastness—Part E01 : Colour fastness to water* (MOD)

2 Normative references The following standards contain provisions which, through reference in this Standard, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS G 4303 *Stainless steel bars*

JIS L 0801 *General principles of test methods for colour fastness*

JIS L 0803 *Standard adjacent fabrics for staining of colour fastness test*

JIS L 0804 *Grey scale for assessing change in colour*

JIS L 0805 *Grey scale for assessing staining*

3 Summary In this test, composite specimens are treated with water, based on the specified method, then treated under pressure using a perspiration tester, and dried, and the change in colour of each specimen and the staining of the standard adjacent fabric are assessed by comparing with the grey scale for assessing change in colour and for assessing staining or by obtaining the rating of change in colour and staining using the instrument and determining the colour fastness.

4 Apparatus and materials For the apparatus and materials, the following shall be used.