

JIS

JAPANESE INDUSTRIAL STANDARD

Plastic Table Wares

☞ JIS S 2029—1984

Translated and Published

by

Japanese Standards Association

Translation without guarantee
In the event of any doubt arising, the original
standard in Japanese is to be evidence



JAPANESE INDUSTRIAL STANDARD

J I S

Plastic Table Wares

S 2029-1984

1. Scope

This Japanese Industrial Standard specifies the plastic table wares, hereinafter referred to as the "table wares". In this case, it contains coated table wares. However, those to be temporally used, those for electronic ovens, sealing vessels and those specified in JIS S 2047 are excepted.

2. Definitions

Main definitions used in this standard shall be in accordance with JIS K 6900 and JIS K 5500, and others shall be as follows:

- (1) sealing vessel The vessel so constructed that liquid is hardly leaked when transported.
- (2) synthetic resin composites The materials compounded with dispersing agents of inorganic or organic matter (talc powder, calcium carbonate powder, glass fiber, chips and shavings, etc.) to improve its physical properties using synthetic resin as matrix.

Applicable Standards: See page 12.

3. Classification

The classification of table wares shall be as given in Table 1.

Table 1

Classification	Division by boil resistance	Symbol
Wooden bowl	No change by boil	A
	Though changes by boil, no change by pouring boiled water	B
Porcelain bowl	No change by boil	A
	Though changes by boil, no change by pouring boiled water	B
Dish	No change by boil	A
	Though changes by boil, no change by pouring boiled water	B
Cup	No change by boil	A
	Though changes by boil, no change by pouring boiled water	B
Lunch box	No change by boil	A
	Though changes by boil, no change by pouring boiled water	B

4. Quality

4.1 Sanitation The table wares shall conform to the Food Sanitation Law (SHOWA 22nd (1947), Law Number 233). However, for coated table wares, it shall apply also to their substrates.

4.2 Appearance and Construction The appearance and construction of table ware shall conform to the following:

- (1) Not to have cuts, cracks, fissures and insufficient molding.
- (2) Not to be striking of practical defects such as foreign matters, bubble, mold mark, sink mark, weld mark, flow mark, burr and others.
- (3) Not to be striking of soils unable to be wiped off with wet cloth.
- (4) Not to be striking of discoloration, fading, irregular colour (except that aiming at decoration), hazing and others.
- (5) To be good of decoration coating and drawing pattern.