



NACE TM0284-2016
Item No. 21215

Test Method

Evaluation of Pipeline and Pressure Vessel Steels for Resistance to Hydrogen-Induced Cracking

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International *FirstService* Department, 15835 Park Ten Place, Houston, Texas 77084-5145 (telephone +1 281-228-6200).

Approval 2016-3-22
Revised 2011-10-28
Revised 2003-01-17
Revised 1996-Mar-30
Reaffirmed 1987-Mar
Approved 1984-Feb
ISBN: 1-57590-163-3
NACE International
15835 Park Ten Place
Houston, TX 77084-5145
+1 281-228-6200
© 2016 NACE International

This is a preview. [Click here to purchase the full publication.](#)

Foreword

Absorption of hydrogen generated by corrosion of steel in a wet hydrogen sulfide (H_2S) environment can have several effects that depend on the properties of the steel, manufacturing or forming processes, the characteristics of the environment, and other variables. One adverse effect observed in pipeline and pressure vessel steels is the development of cracks along the rolling direction of the steel. Cracks on one plane tend to link up with the cracks on adjacent planes to form steps across the thickness. The cracks can reduce the effective wall thickness until the pipeline or pressure vessel becomes overstressed and ruptures. Cracking is sometimes accompanied by surface blistering. Several service failures attributed to such cracking have been reported.^{1,2}

The terms *stepwise cracking* (SWC), *hydrogen pressure cracking*, *blister cracking*, and *hydrogen-induced stepwise cracking* have been used in the past to describe cracking of this type in pipeline and pressure vessel steels, but are now considered obsolete. The term *hydrogen-induced cracking* (HIC) has been widely used for describing cracking of this type, and has been adopted by NACE International. Therefore, it is used throughout this standard test method.

HIC is related to hydrogen blistering, which has been recognized since the 1940s as a problem in pressure vessels handling sour products.³ It was not until much later, however, that HIC gained wide recognition as a potential problem in pipelines. As a result of pipeline failures experienced by two companies in the early 1970s, several companies began investigating the cracking and publishing results of tests on various steels. Many investigators found, however, that they could not reproduce published test results. It was eventually determined that lack of reproducibility resulted largely from differences in test procedures. Consequently, NACE Unit Committee T-1F, "Metallurgy of Oilfield Equipment," established Task Group (TG) T-1F-20, "Stepwise Cracking of Pipeline Steels," to study the problem and prepare a standard test method.

This standard was originally prepared in 1984 to provide a standard set of test conditions for consistent evaluation of steel pipes and for comparison of test results from different laboratories. Subsequently, the concern for HIC damage turned to steel plates used for pressure vessels. Requirements for testing steel plates for resistance to HIC were included in this standard in 1996. More recently, concern for HIC damage in steel fittings and flanges used in pipelines and pressure vessels led to their inclusion in the 2011 revision of this standard. Therefore, the scope of this standard now includes the testing of steels furnished in the form of pipes, plates, fittings, and flanges for use in fabricating pipelines and pressure vessels. In the 2016 revision of this standard, Fitness-For-Purpose testing in an alternative test solution, to be used with gas containing mixtures of H_2S and CO_2 , was included to assess HIC damage under mildly sour test conditions with reduced partial pressure of H_2S in a range of pH values.

Test conditions are not designed to simulate any particular pipeline or process operation, even though in Fitness-for-Purpose tests, partial pressures of H_2S and pH values appropriate to the intended application must be selected. The test is intended to evaluate resistance to HIC only, and not to other adverse effects of sour environments such as sulfide stress cracking (SSC), pitting, or mass loss from corrosion.

This test may be used for many purposes, and the applications of the results are beyond the scope of this standard. Those who use the test should be aware that in some cases, test results can be influenced by variations in properties among different locations in a single length of pipe or individual plate, fitting, or flange, as well as by variations within a heat of steel. When the test is used as a basis for purchasing, the number and location of test specimens must be carefully considered.⁴ This standard is intended for end users, manufacturers, fabricators, and testing laboratories.

This standard was originally prepared by TG T-1F-20 in 1984. It was revised in 1996 by TG T-1F-20, and in 2003, 2011, and 2016 by TG 082, "Stepwise Cracking of Pipeline Steels," which is administered by Specific Technology Group (STG) 32, "Oil and Gas Production—Metallurgy" and sponsored by STG 34, "Petroleum Refining and Gas Processing," and STG 62, "Corrosion Monitoring and Measurement—Science and Engineering Applications." It is issued by NACE under the auspices of STG 32.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*. The terms *shall* and *must* are used to state a requirement, and are considered mandatory. The term *should* is used to state something good and is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.